



# **Federal Specification A-A-2886B Type I**

## **Characteristics:**

- Good bead adhesion
- Spreading rate of 350 linear feet per gallon of 4-inch line
- Spreading rate of 110 - 130 square feet per gallon
- Can be applied with standard striping equipment
- Easy clean-up with Mineral Spirits or VM&P Naphtha

## **Cautions:**

- May bleed on fresh asphalt or sealcoated surfaces - See "Application Procedures"
- This paint may lift improperly aged or inferior asphalt pavements
- Keep away from all heat sources - Flammable

<b>Specifications</b>	
Viscosity: 70 to 85 Krebs Units	Total Solids: 70 % minimum
Weight per gallon: 12.50 minimum	Solvent Type: VM&P Naphtha
Dry to NPU: 15 to 30 minutes track free at 15 mils wet	Shelf Life: 9 months minimum properly stored
Vehicle Type: Alkyd Resin	

**Safety Coatings, Inc.**

20180 Safety Lane

Post Office Box 399

Foley, AL 36536-0399

Phone: (251) 943-1638

Fax: (251) 943-3689

Website: [www.safetycoatings.com](http://www.safetycoatings.com)

E-mail: [info@safetycoatings.com](mailto:info@safetycoatings.com)