



Hi Build

Durable Waterborne Traffic Paint

TTP-1952 E Type III

Characteristics:

- Low VOC
- Excellent initial and long term retroreflectivity (works best with big beads)
- Can be applied with standard waterborne striping equipment with no modifications
- Can be used to refurbish existing thermoplastic lines
- Lower cost than other durable products
- Excellent for crosswalks and legend markings
- Can be applied at films up to 30 mils wet without cracking
- 2 to 3 years durability
- Spreading rate of 180 to 200 linear feet per gallon of 4-inch line

Cautions:

- CANNOT be used in galvanized, brass, aluminum, or steel equipment –
- Recommend stainless steel or plastic components
- Keep from freezing
- Addition of water or other soluble solvents will adversely affect dry time
- All equipment should be cleaned before paint dries

Specifications	
Viscosity: 85 to 95 Krebs Units	Total Solids: 75 % minimum
Weight per gallon: 13.0 minimum	Volume Solids: 60 % minimum
Dry to NPU: 3 to 10 minutes track free at 25–30 mils wet	Shelf Life: 1 year minimum properly stored
Vehicle Type: Patented crosslinking technology acrylic binder	

Safety Coatings, Inc.

20180 Safety Lane

Post Office Box 399

Foley, AL 36536-0399

Phone: (251) 943-1638

Fax: (251) 943-3689

Website: www.safetycoatings.com

E-mail: info@safetycoatings.com