



Federal Specification TTP-1952E Type I

Characteristics:

- Lead and Chromate free
- Low VOC; less than 100 grams per liter
- Excellent glass bead retention and night visibility
- Dry through in 2 hours maximum even at high humidity
- Non-flammable
- Non-bleeding
- Spreading rate of 110 to 130 square feet per gallon
- Easy clean-up with soap and water
- Recommended for sealcoated surfaces, airfields, and highways
- 100% Acrylic Binder

Cautions:

- CANNOT be used in galvanized, brass, aluminum, or steel equipment -
- Recommend stainless steel or plastic components
- Keep from freezing
- Addition of water or other soluble solvents will adversely affect dry time
- All equipment should be cleaned before paint dries

Specifications	
Viscosity: 80 to 90 Krebs Units	Total Solids: 77 % minimum
Weight per gallon: 13.50 minimum	Water resistance: 2 hours minimum drying at temperatures above 50 degrees F and humidity below 80% before exposure to moisture
Dry to NPU: 1 to 3 minutes track free at 15 mils wet	
Vehicle Type: 100% Acrylic fast release resin	Shelf Life: 1 year minimum properly stored

Safety Coatings, Inc.

20180 Safety Lane
Post Office Box 399
Foley, AL 36536-0399

Phone: (251) 943-1638

Fax: (251) 943-3689

Website: www.safetycoatings.com

E-mail: info@safetycoatings.com